

試驗報告



報告編號：HV-16-06330X

頁 數：1 OF 2

報告日期：106 年 02 月 21 日

委 託 單 位：交泰興有限公司
 地 址：台北市仁愛路二段 11 號 3 樓
 供 應 廠 商：KEIMFARBEN GmbH
 原 產 國：德國
 品 名 稱：KEIM Optil 內裝薄塗材 Si
 品 型 號：White
 送 驗 人 員：交泰興有限公司(吳瑞婷)
 收 件 日 期：105 年 10 月 27 日
 試 驗 日 期：105 年 10 月 27 日~106 年 02 月 20 日
 備 註：
 1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
耐變褪色性(WV type, 48 h)	CNS 8082(2010)/	無龜裂及剝離
灰色標	CNS 3839(1994)	色標號碼 5
軟度變化(%)	CNS 8082(2010)	1.15
耐燃性		註 4.

註：1.本試驗報告耐變褪色性、灰色標、軟度變化試驗委託 SGS 材料及工程實驗室-高雄執行，
 耐燃性試驗委託 SGS 材料及工程實驗室-台中執行。

2.耐變褪色性試驗條件：

濾鏡：密閉式

使用光源：Ultraviolet Carbon Arc

測試條件：黑板溫度： $(63 \pm 3)^\circ\text{C}$ 試驗槽溫度： $(42 \pm 3)^\circ\text{C}$ 相對濕度： $(30 \pm 5)\% \text{R.H.}$

測試週期：持續照光不噴水

3.試驗樣品為單液型，耐燃性試驗試片由顧客提供。

規範要求值僅供參考，合格之判定以委託單位實際要求為準。


 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.